FOTHERGILL COATED FABRICS LTD

PRODUCT SPECIFICATION

Mesh

PTFE Coated, Aramid Fabric

Properties	Typical Range		Test Method
Thickness - mm	0.83	1.030	ASTM D1777
Weight - g/m^2	245	445	BS 3424: Part 3
Colour	Various		
Aperture - mm	2x2	5x5	
PTFE - %	28	45	BS 3424: Part 3
Warp Tensile Strength - N/5cm	3000	3700	EN ISO 1421
Surface Resistance - Ohms/Sq	Conductive	Insulative	ASTM D4496-98
Typical Temperature Range - °C	-150	+260	

This product complies wih European Union Regulation (EC) 1907/2006 (REACH) and does not contain Substances of Very High Concern (SVHC). This material does not contain banned substances as described in the RoHS directive and will not affect RoHS compliance

Note: The Nominal values are typical and not intended as a specification and should be considered as a guide only. Contact our sales team with the details of your application. Fothergill Coated Fabrics reserves the right to alter any elements quoted in the above specification without prior notice. The product's suitability for all applications is at the user's discretion, samples for evaluation are available on request.